



Douglas Barwick Inc.



Stainless Steel Piping

Tuyauterie en Acier Inoxydable

IPS PIPE
SCH 5S and 10S

TUYAU IPS
SCH 5S et 10S

ASME SA 312 / ASTM A 312



IPS nom. / dia.	O.D. / D.E. in. / po.	SCHEDULE 5S		SCHEDULE 10S		SCHEDULE 40S		SCHEDULE 80S	
		WALL / MUR in. - po.	WEIGHT/POIDS lb./ft. - lb./pi.	WALL / MUR in. - po.	WEIGHT/POIDS lb./ft. - lb./pi.	WALL / MUR in. - po.	WEIGHT/POIDS lb./ft. - lb./pi.	WALL / MUR in. - po.	WEIGHT/POIDS lb./ft. - lb./pi.
3/4	1.050	0.065	0.684	0.083	0.857	0.113	1.131	0.154	1.474
1	1.315	0.065	0.868	0.109	1.404	0.133	1.679	0.179	2.172
1 1/4	1.660	0.065	1.107	0.109	1.806	0.140	2.273	0.191	2.997
1 1/2	1.900	0.065	1.274	0.109	2.085	0.145	2.718	0.200	3.631
2	2.375	0.065	1.604	0.109	2.638	0.154	3.653	0.218	5.020
2 1/2	2.875	0.083	2.475	0.120	3.531	0.203	5.793	0.276	7.661
3	3.500	0.083	3.030	0.120	4.330	0.216	7.580	0.300	10.250
3 1/2	4.000	0.083	3.505	0.120	5.019	0.226	9.194		
4	4.500	0.083	3.915	0.120	5.613	0.237	10.790	0.337	14.980
5	5.563	0.109	6.409	0.134	7.842	0.258	14.620		
6	6.625	0.109	7.585	0.134	9.290	0.280	18.970	0.432	28.570
8	8.625	0.109	10.010	0.148	13.520	0.322	28.820		
10	10.750	0.134	15.340	0.165	18.830	0.365	40.480		
12	12.750	0.156	21.180	0.180	24.390	0.375	49.560		
14	14.000	0.156	22.280	0.188	27.990	0.375	56.904		
16	16.000	0.165	28.170	0.188	32.050	0.375	65.021		
18	18.000	0.165	31.720	0.188	36.100	0.375	73.139		
20	20.000	0.188	40.150	0.218	46.490	0.375	81.257		
22	22.000	0.188	44.210	0.218	51.190	0.375	89.374		
24	24.000	0.218	55.890	0.250	64.010	0.375	97.492		
30	30.000	0.250	80.180	0.312	99.950	0.375	121.844		